## PRODUCT DATA SHEET

# Chromalite<sup>®</sup> CGA50x2

Gel Strong Base Anion Activated Styrene/ Polydivinylbenzene Copolymer Chromalite CGA50x2 is a chromatographic anion exchange resin with a polymer designed for small organic and inorganic compound separation and purification. It contains 50 m styrenic resin beads crosslinked with 2% divinylbenzene (DVB). Our <u>proprietary</u> <u>manufacturing method</u> creates perfectly spherical beads with exceptional kinetic and packing properties.

Unlike similar products on the market, Chromalite CGA and CGC resins are supplied in highly pure form (very low extractables content) and do not require pre-treatment. As such they are suitable for pharmaceutical applications.

Equivalent to:

- Dowex® 1X2 200-400mesh (Dow)

Note:

CGA resins occasionally exhibit an amine odour after prolonged storage (this will not affect performance).

In such cases it is recommended to rinse the affected resin with sufficient volumes of water to remove the odour before putting the resin into service.

#### **PRINCIPAL APPLICATIONS**

- Ion exchange chromatography
- Desalting of biomolecules after fermentation
- Suitable for inorganic, organic and biological molecule separation

#### **ADVANTAGES**

- High chemical stability
- Low capacity
- Small particle size for high performance
- High purity
- Exceptional kinetic and packing properties

#### **REGULATORY APPROVALS**

- Compliant with FDA regulation 21 CFR 173.25
- Compliant with ResAP(2004) 3
- Kosher
- Halal
- TSE/BSE/GMO free

### **TYPICAL PACKAGING**

- 250 g
- 1 kg

## **TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:**

Supplied as	Wet in CI- form
Volume capacity (min.)	0.6 eq/l
Weight capacity (min.)	4 eq/Kg
Particle size (90% in Range)	35 - 75 μm



Americas T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com **EMEA** T +44 1443 229334 F +44 1443 227073 europe@purolite.com Asia Pacific T +86 571 876 31382 F +86 571 876 31385 asiapacific@purolite.com

Particle size (90% in the range)	200 - 400 mesh
Mean Diameter	50 - 60 µm
Uniformity Coefficient (max.)	< 1.5
Total moisture	70 - 85 %
pH limit stability	1 - 14
Optimal storage condition	2 - 20 °C
Ionic Form	CI-
Expiry date (from date of manufacture)	5 years
% Crosslinking	2



Americas T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com **EMEA** T +44 1443 229334 F +44 1443 227073 europe@purolite.com **Asia Pacific** T +86 571 876 31382

F +86 571 876 31385

© 2020 Purolite

purolite.com

asiapacific@purolite.com April 2, 2020 | Page 2 of 2