PRODUCT DATA SHEET

Chromalite[®] CGC50x4

Gel Strong Acid Cation Activated Styrene/ Polydivinylbenzene Copolymer Chromalite CGC50x4 is a chromatographic cation exchange resin designed for small organic and inorganic compound separation and purification polymer. It contains 50 m styrenic resin beads crosslinked with 4% divinylbenzene (DVB). Our <u>proprietary</u> manufacturing method creates perfectly spherical beads with exceptional kinetic and packing properties.

Unlike similar products on the market, our Chromalite CGA and CGC resins are supplied in highly pure form (very low extractables content) and do not require pre-treatment. As such they are suitable for pharmaceutical applications.

Equivalent to:

- Dowex; 50WX4 200-400 mesh (Dow)

Note:

CGC resins occasionally exhibit colour release into surrounding water after prolonged storage (this will not affect performance).

In such cases it is recommended to rinse the affected resin with sufficient volumes of water to remove this colour release before putting the resin into service.

PRINCIPAL APPLICATIONS

- Ion exchange chromatography
- Desalting of biomolecules after fermentation
- Suitable for inorganic, organic and biological molecule separation

ADVANTAGES

- High chemical stability
- Small particle size for high performance
- High purity
- Exceptional kinetic and packing properties

REGULATORY APPROVALS

- Compliant with FDA regulation 21 CFR 173.25
- Compliant with ResAP(2004) 3
- Halal
- Kosher
- TSE/BSE/GMO free

TYPICAL PACKAGING

- 250 g
- 1 kg

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Orange to dark brown spherical beads
Functional Group	Sulphonic acid
Supplied as	Wet in H+ form



Americas T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com **EMEA** T +44 1443 229334 F +44 1443 227073 europe@purolite.com Asia Pacific T +86 571 876 31382 F +86 571 876 31385 asiapacific@purolite.com

Volume capacity (min.)	1.1 eq/l
Weight capacity (min.)	5 eq/Kg
Particle size (90% in Range)	35 - 75 μm
Particle size (90% in the range)	200 - 400 mesh
Mean Diameter	45 - 55 μm
Uniformity Coefficient (max.)	< 1.5
Total moisture	60 - 75 %
pH limit stability	1 - 14
Optimal storage condition	2 - 20 °C
Ionic Form	H+
Expiry date (from date of manufacture)	5 years
% Crosslinking	4



Americas T +1 610 668 9090 F +1 610 668 8139 americas@purolite.com **EMEA** T +44 1443 229334 F +44 1443 227073 europe@purolite.com **Asia Pacific** T +86 571 876 31382

F +86 571 876 31385

purolite.com

asiapacific@purolite.com April 2, 2020 | Page 2 of 2